

940



Typical Physical Properties

Product Code	Product Description	Color Index	Pigment (%)	Avg. Density (kg/m ³)	Weather Fastness		Light Fastness	
					Fulltone	Red. 1/25	Fulltone	Red. 1/25
940-0001 TWK	White	PW 6	70	2170	5	5	8	8
940-0401 QMK	Magenta	PR 122	13	1060	4-5	4	7d	8
940-0740 REX	HS Red	PR 254	36	1160	4-5	4	8	8
940-0901 ORK	Orange	PO 36	27	1150	5	3-4	8	7-8
940-1001 ROK	Red Iron Oxide	PR 101	65	2180	5	5	8	8
940-1801 YOK	Yellow Iron Oxide	PY 42	56	1840	5	5	8	8
940-2040 YRX	HS Yellow R/S	PY 139	38	1190	4	3-4	8	8
940-2801 YGK	Yellow G/S	PY 139 / PY 184	44	1390	4-5	3 / 4-5	8 / 8	7-8 / 8
940-5501 PGK	Phtalo Green	PG 7	25	1190	5-	5-	8	8
940-7201 PBK	Phtalo Blue	PB 15:4	19	1120	5-	5-	8	8
940-8801 CVK	Carbazole Violet	PV 23	8	1080	4-5	4	8	7-8
940-9440 QVX	HS Quinacridone Violet	PV 19	23	1090	3d	3-4	7d	7-8
940-9901 LBK	Lamp Black	PBk 7	4	1265	5	5	8	8
940-9902 LBX	HS Lamp Black	PBk 7	24	1150	5	5	8	8

All data obtained from pigment suppliers, individual testing is recommended.

Weather fastness is measured on scale 1 to 5, where 1 is severe change and 5 is no change (d = color turns darker).

Light fastness is measured on scale 1 to 8, where 1 is severe change and 8 is no change (d = color turns darker).

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.